

Circle offset Premium White 135cie

Technical Specifications

Substance	gsm	70	80	90	100	120	140	160	200	250	300	350	400	NF EN ISO 536
Thickness	µm	88	101	113	125	150	171	192	239	288	345	403	460	NF EN ISO 534
Bulk	cm ³ /g	1.25	1.26	1.26	1.26	1.25	1.22	1.20	1.20	1.15	1.15	1.15	1.15	NF EN ISO 534
Whiteness	CIE	135	135	135	135	135	135	135	135	135	135	135	135	NF ISO 11475
	ISO	100	100	100	100	100	100	100	100	100	100	100	100	ISO 2470-2
Bendsten roughness	ml/min	230	230	230	230	230	230	230	230	230	230	230	230	ISO 8791-2
Absolute humidity	%H ₂ O	5	5	5	5	5	5.5	5.5	5.5	6	6	6	6	NF EN ISO 20287
Relative humidity	% in the air	40	38	38	38	38	44	44	44	48	48	48	48	Sword measurement
Opacity	%	90	93	95	96	98	95	96	>99	>99	>99	>99	>99	NF ISO 2471
Permanence	DIN 6738 CL 24-85													

*These values are not contractual.
Revision date : 29/04/2020*

Labels

- FSC®
- EU Ecolabel
- Blauer Engel