

BASIX LUXE OFFSET VERGE - GEVERGEERD

Common Attributes	Units	Test Method	90gsm	100gsm	120gsm	170gsm	250gsm	320gsm	350gsm	400gsm
Wood Pulp Bleach Type			ECF Woodfree Virgin Pulp - FSC certified							
Printing Process Suitability			Litho, Silk Screen, Dry Offset (Toray), Blind Embossing, (Hot Foil Blocking, Die Stamping - image and paper texture							
Mono Laser Guaranteed			✓			✗	✗	✗	✗	
Colour Laser Guaranteed			✗	✗	✗	✗	✗	✗	✗	
Mono Ink Jet Guaranteed			✓	✓	✓		✗	✗	✗	
Colour Ink Jet Guaranteed			✓	✓	✓		✗	✗	✗	
Recommended p.H. of Fount solution			5.5 +/- 0.5							
Surface p.H.		TAPPI 529OM	7.5 (5 for the shades: Pale Grey, Le Rouge, Le Bleu, Le Noir)							
Non Aging Credentials		ISO 9706	Yes (Except for Pale Grey, Le Rouge, Le Bleu, Le Noir)							
Environmental Label		ISO 14001	Yes							
Quality Management		ISO 9001:2000	Yes							
Moisture Content	%	ISO 287	6,5	6,5	6,5	6,5	6,5	6,5	6,5	6,5
Relative Humidity	%	TAPPI T502	40-60	40-60	40-60	40-60	40-60	40-60	40-60	40-60

Laid - Gevergeerd

Caliper	µm	ISO534	135		180		300		435	
Bright White Opacity	%	ISO2471	90		93.5					
Bendtsen Roughness	ml/min	ISO2494	900		1200		1300		1300	
Kodak Stiffness	M Direction	ISO5629	0.5		1.5		9.0		24.5	
	C Direction		0.3		0.8		5.5		13.5	

These specifications are the property of Arjo Wiggins Fine Papers Ltd and may be changed without prior notice. They are target values only for use as a guide.

Common Attributes	Units	Test Method	90gsm	100gsm	120gsm	170gsm	250gsm	320gsm	350gsm	400gsm
-------------------	-------	-------------	-------	--------	--------	--------	--------	--------	--------	--------