

ETIBULK



Grammatura Substance	ISO 536	g/m ²	80	85	90	100	115
Spessore Caliper	ISO 534	µm	78	82	86	95	108
Ruvidita' Bendtsen Roughness Bendtsen	ISO 8791-2	ml/min	30	30	30	30	30
Ruvidita Bendtsen retro Roughness Bendtsen back side	ISO 8791-2	ml/min	160	160	180	180	200
Lucido Gardner Gloss Gardner	ISO 8254-1	%	55	55	55	55	55
Bianco Photovolt Photovolt Brightness	ISO 2470	%	88	88	88	88	88
Opacità Photovolt Opacity	ISO 2471	%	92	93	94	95	96
Cobb 60 Cobb 60	ISO 535	g/m ²	27	27	27	27	27
Cobb 60 retro Cobb 60 back side	ISO 535	g/m ²	25	25	25	25	25
Finitura Finishing	Gloss						
Tipo di stampa Printing methods	Tipo Offset Sheet-fed offset						
Applicazioni End uses	Etichette per barattoli Jar and can labels, personalizzazione di imballi per alimenti (es: contenitori per uova) personalization of packaging for food products (

I valori relativi ai singoli prodotti sono forniti a titolo esemplificativo e possono essere soggetti a modifiche senza preavviso. Ogni valore è soggetto a determinate tolleranze.
 Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Carte per etichette e rivestimento scatole
Paper for labels and box wrapping

MonoPatinata
One-side coated paper

e.g. egg containers), rivestimento di scatole box coverings, incarto per cioccolato chocolate wrappers, confezionamento e avvolgimento di pacchetti soft di sigarette production and wr

apping of soft cigarette packets.