

**Tipo carta:** myKingdom XT-S WM High White  
FSC® certified (FSC-C012975)

**Grammatura:** 100

**Type of paper**

**Basis weight**

Caratteristiche della carta <i>Paper properties</i>	unità <i>unit</i>	Minimo <i>minimum</i>	Obbiettivo <i>Target</i>	Massimo <i>maximum</i>	Metodo <i>Method</i>
Grammatura <i>Basis weight</i>	g/m <sup>2</sup>	95	100	105	MCM-003 (ISO 536)
Spessore <i>Caliper</i>	µm	103	<b>110</b>	117	MCM-004 (ISO 534)
Grado di bianco ISO (Filtro Tappi 457) <i>Brightness ISO (Tappi filter 457)</i>	%	91,0	93,0	***	MCM-078 (ISO 2470)
Opacità (fondo carta) <i>Opacity (paper backing)</i>	%	90,0	93,0	***	MCM-036 (ISO 2471-77)
Liscio Bendtsen lato tela <i>Smoothness Bendtsen wire side</i>	ml/min	40	60	90	MCM - 016 (ISO 2494)
Liscio Bendtsen lato ballerino <i>Smoothness Bendtsen felt side</i>	ml/min	40	60	90	MCM - 016 (ISO 2494)
Assorbimento d'acqua (Cobb <sub>60</sub> ) fronte <i>Water absorption (Cobb<sub>60</sub>) top</i>	g/m <sup>2</sup>	20	25	30	MCM - 011 (ISO 535)
Assorbimento d'acqua (Cobb <sub>60</sub> ) retro <i>Water absorption (Cobb<sub>60</sub>) back</i>	g/m <sup>2</sup>	19	24	29	

This product is made of material from well-managed FSC® - certified forests, recycled materials, and other controlled sources.

I valori sopra riportati sono quelli tipici di produzione / The values given above are typical of the production process  
Documento informativo a distribuzione non controllata / Informative document of which distribution is not controlled