

**TECHNICAL DATA SHEET**
**DIN EN ISO 7823-2**

<b>GENERAL</b>			
<b>Property</b>	<b>Method</b>	<b>Unit</b>	<b>CRYLON®</b>
Density	DIN EN ISO 1183	g/cm <sup>3</sup>	1.19
Water absorption_24h/23°C_50x50x4mm <sup>3</sup>	DIN EN ISO 62 – Method 1	%	0.2
Ball indentation hardness	DIN EN ISO 2039-1	MPa	235
Forming temperature air pressure		°C	140 - 160
Forming temperature vacuum		°C	160 - 190
Moulding shrinkage		%	0.5 – 0.8
<b>MECHANICAL</b>			
<b>Property</b>	<b>Method</b>	<b>Unit</b>	<b>CRYLON®</b>
Tensile strength	DIN EN ISO 527-2	MPa	70
Elongation at break	DIN EN ISO 527-2	MPa	4
Tensile modulus	DIN EN ISO 527-2	MPa	3200
Flexural strength	DIN EN ISO 178	MPa	115
Flexural modulus	DIN EN ISO 178	MPa	3300
Impact strength Charpy unnotched	DIN EN ISO 179-1	kJ/m <sup>2</sup>	17
Impact strength Charpy notched	DIN EN ISO 179-1	kJ/m <sup>2</sup>	2
<b>OPTICAL</b>			
<b>Property</b>	<b>Method</b>	<b>Unit</b>	<b>CRYLON®</b>
Light transmission (3 mm)	DIN 5036-3 / DIN EN ISO 13468-2	%	92
Refractive index	DIN EN ISO 489	n <sub>D</sub> <sup>20</sup>	1.492
Total solar energy transmission (g – Wert)	DIN EN 410	%	86.5
Gloss value	DIN 67530		>100

**TECHNICAL DATA SHEET**
**DIN EN ISO 7823-2**

<b>THERMAL</b>			
<b>Property</b>	<b>Method</b>	<b>Unit</b>	<b>CRYLON®</b>
Vicat temperature (B 50) (Pre-treatment 16h at 80°C)	DIN EN ISO 306	°C	105
Specific heat capacity	DIN EN ISO 11357-4	J/gK	1.47
Linear thermal expansion	DIN 53752 ISO 11359-2	mm/m x °C	0.07
Thermal conductivity	DIN 52612 DIN EN ISO 22007-1	W/mK	0.18
Service temperature continuous use		°C	70
Max. temperature short term use		°C	90
Degradation temperature		°C	> 280
<b>ELECTRICAL</b>			
<b>Property</b>	<b>Method</b>	<b>Unit</b>	<b>CRYLON®</b>
Surface resistivity	IEC 60093 DIN EN 62631-1-3-2	Ω	3x10 <sup>15</sup> - 3x10 <sup>16</sup>
Volume resistivity	IEC 60093 DIN EN 62631-1-3-1	Ω x m	1x10 <sup>13</sup> - 5x10 <sup>13</sup>
Electrical strength	IEC 60243-1 DIN EN 60243-1	kV/mm	10
Dielectric strength	IEC 60243-1 DIN EN 60243-1	kV/mm	30
Dielectric dissipation factor 50 Hz / 1 KHz / 1 MHz	DIN 53483-2		0.06 / 0.04 / 0.02
Relative permittivity 50 Hz / 1 KHz / 1MHz	DIN 53483-2		2.7 / 3.1 / 2.7

**TECHNICAL DATA SHEET**
**DIN EN ISO 7823-2**

<b>Other</b>			
<b>Property</b>	<b>Method</b>	<b>Unit</b>	<b>CRYLON®</b>
Fire resistance	UL94	classification	HB
Fire performance	CPD 305/2011 DIN EN 13501-1	classification	E No burning droplets
Food contact - GMP	EU directive 1935/2004 Regulation 10/2011	---	Conform
Biocompatibility	DIN ISO 10993-5	---	Not cytotoxic

Note: Technical data of our products are typical ones; the actually measured values are subject to production variations.