




Technical Data Sheet

Di Pro 300gsm

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	300 +/- 8
Thickness	ISO 534	µm	300 +/- 5
Bulk	ISO 534		1,0
Moisture Content	ISO 287	%	4,5 +/- 0,6
Smoothness	ISO 5627	Bekk sec	75 +/- 10
Formation	Kajaani	Kajaani index	110
Whiteness	ISO 11475	CIE	168 +/- 2
Brightness D65	ISO 2470-2	%	112 +/- 1
Opacity	ISO 2471	%	Min 99
Stiffness MD	ISO 2493	m/N	1500 +/- 40
Stiffness CD	ISO 2493	m/N	940 +/- 30

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:

Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp
ISO 45001 - Health & Safety

The data presented can be changed without notice.

International Paper EMEA
Chaussée de la Hulpe 166
1170 Brussels, Belgium
Tel.: +32 2 774 1211
Fax: +32 2 774 1299
Extract date: 10.03.2020