

JAC SHEETS

JAC TAG FSC® CERTIFIED

Print carrier

Average values

JAC® TAG FSC® Certified is white, wood-free, supercalendered board. It enjoys application wherever a face material of particularly high stability is required. The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

For technical guidance please visit our website under Downloads "Guidelines for use" – Offset printing.

	TAG FSC® Certified
Weight (g/m ²)	170
Thickness (micron)	150
Surface smoothness (PPS)	2.8 µm
Opacity (%)	98
Shelf life of laminate (years) ¹	2

¹ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%

For technical guidance please visit our website under please visit our website under downloads "Guidelines for Use" - Offset printing.

Adhesive

Average values

DURO PLUS is an acrylic dispersion-based adhesive, displaying very good application and processing properties including good to excellent guillotining behaviour and very good UV stability.

It shows good performance on rough and plastic substrates.

	DURO PLUS
Adhesion (N/25 mm) (FTM 2 on st. steel/20 min. bond time)	11
Tack (N/25 mm) (FTM 9 on glass)	15.4
Recommended minimum application temperature (°C)	>+5
Heat resistance up to 24 hrs (°C)	+80
up to 1 hr (°C)	+110
Resistance to cold (°C) ² down to	- 40

¹ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Silicone paper

Average values

B 110 – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized and displays very high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

	B 110
Weight (g/m ²)	86
Thickness (µm)	87

Issue May 2021

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.