



Technical Data Sheet

RICOH PRO-GRAPHIC 250 GSM

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	250 +/- 6
Thickness	ISO 534	µm	250 +/- 5
Bulk	ISO 534		1,00
Moisture Content	ISO 287	%	4,5 +/- 0,5
Smoothness	ISO 5627	Bekk sec	100 +/- 10
Formation	Kajaani	Kajaani index	110
Whiteness	ISO 11475	CIE	168 +/- 2
Brightness D65	ISO 2470-2	%	112 +/- 1
Opacity	ISO 2471	%	Min 98
Stiffness MD	ISO 2493	m/N	1060 +/- 30
Stiffness CD	ISO 2493	m/N	640 +/- 20

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:
 Product is made taking into account requirements of DIN EN 12281
 Product made from ECF Pulp
 ISO 18001 - OHSAS Health & Safety

The data presented can be changed without notice.

International Paper EMEA
 Chaussée de la Hulpe 166
 1170 Brussels, Belgium
 Tel.: +32 2 774 1211
 Fax: +32 2 774 1299
 Extract date: 31.08.2017