# JAC SHEETS JAC ACETATE / ACETATE SILK

# **Print carrier**

JAC® ACETATE SILK - 80120 is an acetate fabric for use on e g. the reverse side of carpets and mattresses and textiles

Offset printing recommended using oxidative drying inks. When screen printed, care should be taken to ensure that only a negligible amount of solvent is used. All printing inks should be tested for suitability prior to use.

The above products are not suitable for outdoor use.

For technical guidance please visit our website under please visit our website under downloads "Guidelines for Use " - Offset printing.

### Average values

	67312	
Weight (g/m²)	120	
Thickness (micron)	119	
Opacity (%)	68	
CIE Whiteness (%)	-	
Shelf life of laminate (years) <sup>1</sup>	2	

 $^{\rm 1)}$  Stored in original packaging a temperature of 22  $\pm$  2°C and a relative humidity of  $50\% \pm 5\%$ 

For information regarding EHS regulation please visit our website under downloads "Guidelines for Use "5.12 Product Compliance JAC® Offset.

# Adhesive

The adhesive is acrylic solvent-based, displaying very good application and processing properties including good to excellent guillotining behavior. Very good UV stability and high temperature resistance.

DURO AL 190 showing high tack and adhesion especially on very difficult surfaces, such as the reverse sides of carpets, mattresses, textiles etc. Not recommended for applications on silk, leather, suede or other sensitive fabrics - can cause staining! Tests for suitability on critical substrates prior to use are recommended.

#### Average values

	DURO AL 190	
Adhesion (N/25 mm) (FTM2 on st.steel/20 min. bond	12	
time)		
Tack (N/25 mm)	13	
(FTM9 on glass)	10	
Recommended minimum	+10	
application temperature (°C)		
Heat resistance		
up to 24 hrs (°C)	+80	
up to 1 hr (°C)	+110	
Resistance to cold (°C) <sup>2</sup>	- 40	
down to		

<sup>2</sup> Not fully resistant until after adhesion reaches full strength – after at least 24 hrs

## **Silicone paper**

B145 - siliconized kraft, wood-free, specialpurpose paper, moisture-stabilized through a special coating on one side. It displays high dimensional stability and excellent flatness.

Average values	
	B 145
Weight (g/m²)	137
Thickness	140

Issue May 2021

#### Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All product are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see https://www.lecta.com/terms JAC\* is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.

