



## Technical Data Sheet

### Di Pro 160 gsm

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m <sup>2</sup>	160+/-2
Thickness	ISO 534	µm	176 +/- 3
Bulk	ISO 534		1,10
Moisture Content	ISO 287	%	5,3 +/- 0,6
Roughness	ISO 8791	Bendtsen ml/min	80 +/- 25
Smoothness	ISO 5627	BEKK sec	65 +/- 15
Whiteness	ISO 11475	CIE	170 +/- 2
Brightness D65	ISO 2470-2	%	113 +/- 1
Opacity	ISO 2471	%	99 +/- 2
Stiffness MD	ISO 2493	m/N	540 +/- 15
Stiffness CD	ISO 2493	m/N	290 +/- 15

#### Production sites:

The production mills operate in compliance with the following standards



#### Special Attributes:



References:  
 Product is made taking into account requirements of DIN EN 12281  
 Product made from ECF Pulp  
 ISO 45001 - Health & Safety

The data presented can be changed without notice.

International Paper EMEA  
 Chaussée de la Hulpe 166  
 1170 Brussels, Belgium  
 Tel.: +32 2 774 1211  
 Fax: +32 2 774 1299  
 Extract date: 10.03.2020