

## TECHNICAL DATASHEET

### Acrylic sheet

#### 1. PRODUCT IDENTIFICATION

---

CRYLON® is the brand name for extruded Polymethyl methacrylate sheets from POLYCASA, standard or high impact. The CRYLON® and High Impact programme offers solutions to both indoor and outdoor applications. As a result of the extrusion process, POLYCASA can offer a variety of colours and designs.

#### 2. CHARACTERISTICS

---

- Good optical properties
- Brilliant surface
- Easy to fabricate, to vacuum form
- Show an exceptional high light transmission
- Good scratch resistance for the standard grade
- High surface hardness for the standard grade
- Good recyclability
- XT and XT High Impact meet all current European food contact legislation and can be used in contact with foodstuffs
- Excellent transparency

#### 3. APPLICATIONS

---

##### Constructional components

- Light domes
- Partition walls
- Door glazing
- Roofing
- Roof hoods for caravans

##### Lighting

- Covers for lighting
- Coffered lighting
- Kitchen lighting
- Illuminated plates

##### Engineering components

- Housing
- Machine covers

##### Advertising and decoration materials

- Letters
- Decorations
- Displays
- Advertising fittings
- Advertising panels

##### Other applications

- Containers
- Lettering templates
- Sign equipment etc.
- Solariums UVT (UV-translucent grade)

#### 4. FABRICATION AND FINISHING TECHNIQUES

---

CRYLON® and CRYLON® High Impact sheets are easy to handle. They can be machined using all the usual methods, such as sawing, milling, drilling, turning, grinding and polishing, and are most suitable for thermoforming.

More detailed information on these items can be found in the "USER GUIDE", available on request.

## TECHNICAL DATASHEET

### Acrylic sheet

#### 5. TECHNICAL DATA

GENERAL				
Property		Method	Units	CRYLON®
	Density	ISO 1183	g/cm <sup>3</sup>	1.19
	Water absorption 24h/23°C – 50x50x4mm <sup>3</sup>	DIN EN ISO 62 Method 1	%	0.2
	Ball indentation hardness	ISO 2039-1	MPa	235
	Forming temperature air pressure		°C	140-160
	Forming temperature vacuum		°C	160-190
	Moulding shrinkage		%	0.5-0.8
MECHANICAL				
	Tensile strength	ISO 527-2	MPa	70
	Elongation at break	ISO 527-2	%	4
	Tensile modulus	ISO 527-2	MPa	3200
	Flexural strength	ISO 178	MPa	115
	Flexural modulus	ISO 178	MPa	3300
	Impact strength Charpy unnotched	ISO 179-1	kJ/m <sup>2</sup>	17
	Impact strength Charpy notched	ISO 179-1	kJ/m <sup>2</sup>	2
THERMAL				
	Vicat temperature (B 50)*	ISO 306	°C	105
	Specific heat capacity	ISO 11357-4	J/gK	1.47
	Linear thermal expansion	DIN 53752	K <sup>-1</sup> *x10 <sup>-5</sup>	7
	Thermal conductivity	DIN 52612	W/mK	0.18
	Service temperature continuous use		°C	70
	Max. temperature short term use		°C	90
	Degradation temperature		°C	>280
OPTICAL				
	Light transmission (3mm)	DIN 5036-3 / EN ISO 13468-2	%	92
	Refractive index	ISO 489	n <sub>D</sub> <sup>20</sup>	1.492
ELECTRICAL				
	Surface resistivity	IEC 60093	Ω	3x10 <sup>15</sup> - 3x10 <sup>16</sup>
	Volume resistivity	IEC 60093	Ω x m	1x10 <sup>13</sup> - 5x10 <sup>13</sup>
	Electrical strength	IEC 60243-1	kV/mm	10
	Dielectric strength	IEC 60243-1	kV/mm	30
	Dielectrical dissipation factor 50 Hz	DIN 53483-2		0.06
	Dielectrical dissipation factor 1 KHz	DIN 53483-2		0.04
	Dielectrical dissipation factor 1 MHz	DIN 53483-2		0.02
	Relative permittivity 50 Hz	DIN 53483-2		2.7
	Relative permittivity 1 KHz	DIN 53483-2		3.1
	Relative permittivity 1MHz	DIN 53483-2		2.7

\*Pre-treatment 16h at 80°C

**Note:** These technical data of our products are typical ones; the actually measured values are subject to production variations.