



## Technical Data Sheet

### RICOH PRO GRAPHICS 200GR

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m <sup>2</sup>	200 +/- 5
Thickness	ISO 534	µm	196 +/- 3
Bulk	ISO 534		0,98
Moisture Content	ISO 287	%	4,6 +/- 0,5
Smoothness	ISO 5627	Bekk sec	135 +/- 20
Formation	Kajaani	Kajaani index	110
Whiteness	ISO 11475	CIE	168 +/-2
Brightness D65	ISO 2470-2	%	112 +/- 1
Opacity	ISO 2471	%	Min 98
Stiffness MD	ISO 2493	m/N	700 +/- 30
Stiffness CD	ISO 2493	m/N	400 +/- 20

#### Production sites:

The production mills operate in compliance with the following standards



#### Special Attributes:



#### References:

Product is made taking into account requirements of DIN EN 12281  
 Product made from ECF Pulp  
 ISO 18001 - OHSAS Health & Safety

The data presented can be changed without notice.

International Paper EMEA  
 Chaussée de la Hulpe 166  
 1170 Brussels, Belgium  
 Tel.: +32 2 774 1211  
 Fax: +32 2 774 1299  
 Extract date: 01.07.2019