



Mirror Product Data Sheet

Delivery Options

Thickness of up	mm	0,3
Width of up to max	mm	1250

Optical Properties

Total light reflection	%	90
Diffuse light reflection	%	≤12
Iridescence Assessment		Absolutely free of interference colors
Corrosion resistance		based on 5% NaCl salt spray test above 167hours

Mechanical Properties

Tensile strength	[MPa]	160-200
Yield strength	[MPa]	145-180
Elongation	%	≥2
Deformation / Bending	Bending radius	≥1.5* gauge of material

Tolerance

Width	mm	+ 0.2/ - 0.2
Length	mm	+ 0.3/ - 0.3