



Technical Data Sheet

Di Pro 100gsm

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	100 +/- 2
Thickness	ISO 534	µm	114 +/- 3
Bulk	ISO 534		1,14
Moisture Content	ISO 287	%	4,4 +/- 0,6
Roughness	ISO 8791	Bendtsen ml/min	80+/- 25
Smoothness	ISO 5627	BEKK sec	65 +/- 15
Whiteness	ISO 11475	CIE	170 +/- 2
Brightness D65	ISO 2470-2	%	113 +/- 1
Opacity	ISO 2471	%	95 +/- 2
Stiffness MD	ISO 2493	m/N	160 +/- 15
Stiffness CD	ISO 2493	m/N	90 +/- 15

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:
 Product is made taking into account requirements of DIN EN 12281
 Product made from ECF Pulp
 ISO 45001 - Health & Safety

The data presented can be changed without notice.

International Paper EMEA
 Chaussée de la Hulpe 166
 1170 Brussels, Belgium
 Tel.: +32 2 774 1211
 Fax: +32 2 774 1299
 Extract date: 10.03.2020